

Pro Emerytex®

Interlam™ Pro Emerytex® is a 4 mil (100µ) monomeric soft calendared PVC laminating film with a matte pebble textured finish, coated on one side with a pressure sensitive acrylic adhesive that is protected by a bleached Kraft release paper coated on both sides with PE and siliconized on the release side. Interlam™ Pro Emerytex® has been tested according to the EN 13036-4 test method and awarded a rating of low slip potential.

- RECOMMENDED FOR LAMINATING MOUNTED PRINTS THAT WILL BE PLACED IN HIGH TRAFFIC INDOOR AND OUTDOOR DISPLAY AREAS
- IDEAL FOR TRADESHOW GRAPHICS, POP DISPLAYS, MOUSE PADS, COUNTER MATS, EVENT SIGNAGE, FLOOR GRAPHICS, AND OTHER SIGNAGE WHERE A SCUFF-RESISTANT FINISH IS REQUIRED
- CAN BE COMBINED WITH DRYTAC'S PRINT MEDIA TO CREATE A SLIP-RESISTANT FLOOR GRAPHICS.
- FILM AND ADHESIVE PROVIDE UV PROTECTION

PROCESS SETTINGS

Equipment Type & Temperature Speed

Roller Laminator
Room temperature
to 104°F (40°C)

1 ft to 8 ft (0.3m to
2.5m) per minute

Press

Not recommended

**For more information,
performance and warranty
guidelines please contact your
local Drytac office.**

© 2025 Drytac Corporation. E&OE.
All other trademarks are the property
of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Matte Pebble Textured Monomeric Soft Calendared PVC
Adhesive	Acrylic (Pressure Sensitive)
Release Liner	2 Side PE Coated, 1 Side Siliconised Kraft

PRODUCT CHARACTERISTICS

Film Thickness	4 mil (100µ) 5 mil
Adhesive Layer	1 mil (25µ) (125µ)
Outdoor Durability	5 Years (Ink Dependent)
Fire Ratings	Class 0 (BS 476 Part 6 and 7) Class 1 or A (ASTM E-84) PASS (CAN/ULC-S102)
Paired Solution Fire Rating	B _{fl} - s1 (EN 13501-1) when paired with Polar Grip print media
FDA Certification	PASS (FDA 21 CFR 177.1975)
Slip Certifications	<ul style="list-style-type: none"> • PTV: Low Slip Potential; Dry: 68 Wet: 48 (ASTM E303-22) • Wet: 45 (HB198:2014 (AS/NZS 4586)) • PTV: Dry: 69 Wet: 45 (EN 16165:2021)
Application Temperature	-4°F (-20°C)
Service Temperature Range	-49°F to 230°F (-45°C to +110°C)
Peel Strength (20 min, FTM1)	11 N/25mm
Shelf Life	2 Years
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

DRYTAC®

Europe

Filwood Road,
Fishponds,
Bristol, BS16 3RY,
United Kingdom
bristol@drytac.com
Tel: +44 (0) 117 958 6500

Canada

30 Driver Road,
Brampton,
Ontario, L6T 5V2,
Canada
toronto@drytac.com
Tel: +1 800.353.2883

USA

5401-B Eubank Road,
Sandston,
Virginia, 23150,
USA
customerservice@drytac.com
Tel: +1 800.280.6013